


GRADING ENVELOPE



C.R Min. 5 Tonne
 S.E Min. Non plastic

PERCENTAGE PASSING British Standard Sieves (Grading)

	AP 40 ———	AP 20 - - - -
19.00 mm	70-87	70-100
9.50 mm	48-68	40-80
4.75 mm	35-54	30-62
2.36 mm	25-41	24-50
1.18 mm	19-32	18-40
600 um	12-26	12-30
300 um	8-20	8-24
150 um	3-15	3-15
75 um	0-11	0-8

Note:

For use as granular Pipe Bedding material AP20 for pipes up to 675ø, and AP40 for 675ø and above.

MANARC
 MANUKAU CITY APPROVED
 REQUIREMENT

DETAIL:
**MELTER SLAG
 GRANULAR PIPE BEDDING**

UPDATED:
OCT 2003

DETAIL No:
MD-9

MANUKAU CITY COUNCIL