


# GRADING ENVELOPE



C.R Min.                    100 kN  
W.R                            CA or Better  
S.E.                            25 min

## PERCENTAGE PASSING (NRB M/3 Grading)

British Standard Sieves (Grading)

65 mm	100
37.5 mm	80-90
19.00 mm	50-70
9.50 mm	30-55
4.75 mm	20-40
2.36 mm	15-30
1.18 mm	10-22
0.6 mm	6-18
0.3 mm	4-14
0.15 mm	2-10
0.075mm	0-7

**MANARC**

MANUKAU CITY APPROVED  
REQUIREMENT

DETAIL:

**65mm SUB-BASECOURSE  
(MEETING TNZ M/3 GRADING)**

UPDATED:

**MAY 1999**

DETAIL No:

**MR-8**

**MANUKAU CITY COUNCIL**